

PCT/EP

91 / 05254



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

REC'D 10 AUG 2001

WIPO

PCT

BEST AVAILABLE COPY

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

00201702.8

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

I.L.C. HATTEN-HECKMAN

DEN HAAG, DEN
THE HAGUE, 06/08/01
LA HAYE, LE



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

**Blatt 2 der Bescheinigung
Sheet 2 of the certificate
Page 2 de l'attestation**

Anmeldung Nr.:
Application no.:
Demande n°: 00201702.8

Anmeldetag:
Date of filing:
Date de dépôt: 12/05/00

Anmelder:
Applicant(s):
Demandeur(s):
Montell Technology Company B.V.
2132 MS Hoofddorp
NETHERLANDS

Bezeichnung der Erfindung:
Title of the invention:
Titre de l'invention:
Pre-polymerized catalyst components for the polymerization of olefins

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:
State:
Pays:

Tag:
Date:
Date:

Aktenzeichen:
File no.
Numéro de dépôt:

Internationale Patentklassifikation:
International Patent classification:
Classification internationale des brevets:

/

Am Anmeldetag benannte Vertragsstaaten:
Contracting states designated at date of filing: AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LU/LU/MC/NL/PT/SE/TR
Etats contractants désignés lors du dépôt:

Bemerkungen:
Remarks:
Remarques:

Printed: 06-08-2001

DESC

EPO - DG 7

12. 05. 2000

00201702

TC 5431

(41)

Title:

Pre-polymerized catalyst components for the polymerization of olefins

12-05-2000

The present invention relates to catalyst components for the preparation of ethylene (co)polymers by using gas-phase, slurry or bulk (co)polymerization processes.

High-yield catalyst components for the polymerization of olefins and in particular for ethylene are known in the art. They are generally obtained by supporting, on a magnesium dihalide, a titanium compound normally chosen from titanium halides alkoxide and haloalcoholates. Said catalyst components are then used together with an aluminum alkyl compound in the polymerization of ethylene. This kind of catalyst components, and the catalysts obtained therefrom, are largely used in the plants for the (co)polymerization of ethylene both operating in liquid phase (slurry or bulk) and in gas-phase. However, the use of the catalyst components as such is not completely satisfactory. Indeed, due to the high reactivity of the ethylene, the kinetic of the polymerization reaction is very high. As a consequence, the catalyst is subject to a very strong tension during the initial stage of polymerization which can cause the uncontrolled breakage of the catalyst itself. This event is the cause of the formation of fines, which, in turn, leads to low bulk density of the polymer and to operating process difficulties.

In the attempt to solve these problems, the catalyst is pre-polymerized under controlled conditions, so as to obtain pre-polymerized catalysts purposed to have good morphology. In fact, it is believed that after the pre-polymerization, the catalysts increase their resistance in such a way that the tendency to break under polymerization conditions is decreased. As a consequence, also the formation of fines would be reduced. In addition, it is hoped that also the bulk density of the final polymers is improved. In principle the catalyst component could be pre-polymerized with any olefin, however, in practice, the non-stereospecific catalysts are always pre-polymerized with ethylene. In fact, in the art it is believed that if prochiral α -olefins like propylene would be pre-polymerized with non-stereospecific catalyst, the high amount of amorphous polymer produced would negatively affect the performance of the catalysts both in terms of activity and morphological properties. The pre-polymerization with ethylene of a non-stereospecific catalyst however does not fully solve the problems mentioned before. In USP 4,325,837 for example, as it is apparent from table 14A and 14B, the use of a non-stereospecific catalyst pre-polymerized with ethylene to an extent of lower than 50%b.w., based on the weight of the total pre-polymerized

(TC 5431 EP)

catalyst, is not always satisfactory because the yields and the morphological properties of the polymer produced with the pre-polymerized catalyst are in certain cases lower than that of the non-pre-polymerized one. In the patent itself it is said (column 37 lines 57-60) that the use of a pre-polymerized catalyst is of no advantage with respect to the non pre-polymerized one. In addition to these problems it must be noted that in view of the very high reactivity of ethylene the pre-polymerization with this monomer can give some difficulties in keeping the mild conditions that are generally used in the pre-polymerization in order to reach the desired properties of the catalyst.

In view of this situation it has now surprisingly been found that by carrying out the pre-polymerization with prochiral monomers it is possible to obtain a catalyst for the polymerization of olefins which is capable to produce polymers with high bulk density, to avoid the problems of formation of fines and that has an activity which is higher than that of the original non pre-polymerized catalyst.

It is therefore an object of the present invention a pre-polymerized catalyst component for the polymerization of ethylene, optionally in mixtures with olefins $\text{CH}_2=\text{CHR}$, wherein R is a C1-C12 alkyl group, characterized by comprising a non-stereospecific solid catalyst component, comprising a titanium compound and a magnesium dihalide, which is pre-polymerized with an alpha olefin $\text{CH}_2=\text{CHR}^1$ wherein R is a C1-C8 alkyl group, to such an extent that the amount of the α -olefin pre-polymer is up to 100g per g of said solid catalyst component.

According to the present invention the term "non-stereospecific solid catalyst component" means a solid catalyst component that gives, under the standard polymerization conditions described below, a propylene homopolymer having an insolubility in xylene at 25°C lower than 90% and preferably lower than 85%.

Preferably, the amount of the α -olefin polymer is less than 15 g and more preferably said amount is less than 5 g per g of solid catalyst component. In the preferred embodiment said amount of the α -olefin polymer is from 0.8 to 4 g per g of solid catalyst component.

The magnesium halides, preferably MgCl_2 , in active form used as a support for Ziegler-Natta catalysts, are widely known from the patent literature. Patents USP 4,298,718 and USP 4,495,338 were the first to describe the use of these compounds in Ziegler-Natta

(TC 5431.EP)

catalysis. It is known from these patents that the magnesium dihalides in active form used as support or co-support in components of catalysts for the polymerization of olefins are characterized by X-ray spectra in which the most intense diffraction line that appears in the spectrum of the non-active halide is diminished in intensity and is broadened to form a halo. The preferred titanium compounds used in the catalyst component of the present invention are those of formula $Ti(OR^{II})_{n-y}X_y$, where R^{II} is a C1-C20 hydrocarbon group X is halogen, n is the valence of titanium and y is a number between 1 and n. Particularly preferred compounds are $TiCl_4$, $TiCl_3$ and Ti-tetraalcoholates or Ti-chloroalcoholates of formula $Ti(OR^{III})_aCl_{n-a}$ where n is the valence of titanium, a is a number comprised between 1 and n, and R^{III} is a C1-C8 alkyl or aryl group. Preferably R^{III} is selected from n-butyl, isobutyl, 2-ethylhexyl, n-octyl and phenyl.

The titanium compound can be pre-formed, or it is produced in-situ by the reaction of a titanium tetrahalide, in particular $TiCl_4$, with alcohols R^nOH or with titanium alkoxides having the formula $Ti(OR^n)_4$.

In the alternative, the titanium tetralkoxides can be caused to react with halogenating compounds such as, for instance, $SiCl_4$, $AlCl_3$, chlorosilanes, Al-alkyl halides to form titanium haloalcoholates. In the latter case, the titanium valence is reduced and titanium haloalkoxides are formed wherein the titanium valence is lower than 4.

The preparation of the solid catalyst component can be carried out according to several methods. According to one of these methods, the magnesium dichloride in an anhydrous state and the titanium compound are milled together under conditions in which activation of the magnesium dichloride occurs. The so obtained product can be treated one or more times for example with an excess of $TiCl_4$ at a temperature between 80 and 135°C. This treatment is followed by washings with hydrocarbon solvents until chloride ions disappeared. According to a further method, the product obtained by co-milling the magnesium chloride in an anhydrous state and the titanium compound is treated with halogenated hydrocarbons such as 1,2-dichloroethane, chlorobenzene, dichloromethane etc. The treatment is carried out for a time between 1 and 4 hours and at temperature of from 40°C to the boiling point of the halogenated hydrocarbon. The product obtained is then generally washed with inert hydrocarbon solvents such as hexane.

(TC 5431.EP)

According to another method, magnesium dichloride is pre-activated according to well-known methods and then treated with an excess of TiCl_4 at a temperature of about 80 to 135°C . The treatment with TiCl_4 is repeated and the solid is washed with hexane in order to eliminate any non-reacted TiCl_4 .

A further method comprises the reaction between magnesium alcoholates or chloroalcoholates (in particular chloroalcoholates prepared according to U.S. 4,220,554) and an excess of TiCl_4 at a temperature of about 80 to 120°C .

According to a preferred general method, the solid catalyst component can be prepared by reacting a titanium compound of formula $\text{Ti}(\text{OR}^n)_x\text{X}_y$, where X, R^n , n, and y have the same meanings described above, with a magnesium chloride deriving from an adduct of formula $\text{MgCl}_2 \cdot p\text{ROH}$, where p is a number between 0.1 and 6, preferably from 2 to 3.5, and R is a hydrocarbon radical having 1-18 carbon atoms. The adduct can be suitably prepared in spherical form by mixing alcohol and magnesium chloride in the presence of an inert hydrocarbon immiscible with the adduct, operating under stirring conditions at the melting temperature of the adduct ($100\text{-}130^\circ\text{C}$). Then, the emulsion is quickly quenched, thereby causing the solidification of the adduct in form of spherical particles. The so obtained adduct can be directly reacted with the Ti compound or it can be previously subjected to thermally controlled dealcoholation ($80\text{-}130^\circ\text{C}$) so as to obtain an adduct in which the number of moles of alcohol is generally lower than 3 preferably between 0.1 and 2.5. The reaction with the Ti compound can be carried out for example by suspending the adduct (dealcoholated or as such) in cold TiCl_4 (generally 0°C); the mixture is heated up to $80\text{-}130^\circ\text{C}$ and kept at this temperature for 0.5-2 hours. The treatment with TiCl_4 can be carried out one or more times.

The preparation of catalyst components in spherical form is described for example in European Patent Applications EP-A-395083 and WO98/44009.

According to a variation of the method described above the preparation of the solid catalyst components can comprise the following steps:

- (a) reacting a compound $\text{MgCl}_2 \cdot m\text{ROH}$, wherein $0.3 \leq m \leq 1.7$ and R is an alkyl, cycloalkyl or aryl radical having 1-12 carbon atoms, with a titanium compound of the formula $\text{Ti}(\text{OR}^n)_x\text{X}_y$, in which b is comprised between 0 and 0.5, y is the valence of titanium, X is halogen and R^n has the meaning given above;

- (b) reacting the product obtained from (a) with an Al-alkyl compound and
- (c) reacting the product obtained from (b) with a titanium compound of the formula $Ti(OR^II)_nX_{y-n}$, in which n, y, X and R^{II} have the meanings explained above.

As mentioned above the compound $MgCl_2 \cdot mROH$ can be prepared by thermal dealcoholation of adducts $MgCl_2 \cdot pEtOH$, having a higher alcohol content.

In the reaction of step (a) ~~the molar ratio Ti/Mg is stoichiometric or higher, preferably this ratio is higher than 3.~~ Still more preferably a large excess of titanium compound is used. Preferred titanium compounds are titanium tetrahalides, in particular $TiCl_4$.

In step (b) the product obtained from (a) is then reacted with an aluminum-alkyl compound. The aluminum alkyl compound is preferably selected from those of formula R_zAlX_{3-z} in which R is a C_1 - C_{20} hydrocarbon group, z is an integer from 1 to 3 and X is halogen, preferably chlorine. Particularly preferred is the use of the trialkyl aluminum compounds such as for example triethylaluminum, triisobutylaluminum, tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum and tris(2,4,4-trimethyl-pentyl)aluminum. Use of tris(2,4,4-trimethyl-pentyl)aluminum is especially preferred. It is also possible to use mixtures of trialkylaluminum compounds with alkylaluminum halides, alkylaluminum hydrides or alkylaluminum sesquichlorides, such as $AlEt_2Cl$ and $Al_2Et_3Cl_3$.

The reaction with the Al-alkyl compound with the product coming from (a) can be carried out in a hydrocarbon solvent at a temperature between $-10^\circ C$ and $130^\circ C$. Preferably the reaction is carried out at a temperature between 40 and $110^\circ C$. The molar ratio between the Al-alkyl compound and the product coming from (a) is not particularly critical. Generally the Al-alkyl compound can be used in molar ratios with the alcohol originally contained in the compound (a) from 0.01 to 100.

In the third step, the solid product coming from (b) is further reacted with a titanium compound of the same formula given above. Preferably, the specific titanium compound and the reaction conditions are similar to those used in the step (a). The use of the catalyst components prepared by this method is preferred.

Moreover, it constitutes a preferred aspect of the invention also the use of catalyst components obtained by another variation of the general method described above and that comprises (a) the thermal dealcoholation of the adducts $MgCl_2 \cdot pEtOH$ until forming adducts

(TC 5431.EP)

in which the alcohol content is reduced to values lower than 2 and preferably comprised between 0.3 and 1.5 mols per mol of magnesium dihalide, (b) the treatment of said thermally dealcoholated adduct with chemical reagents capable of reacting with the OH groups of the alcohol and of further dealcoholating the adduct until the content is reduced to values which are generally lower than 0.5 mols and (c) the reaction of said chemically dealcoholated adduct with a Ti compound of formula $Ti(OR^u)_nX_y$, where X, R^u , n, and y have the same meanings described above. The adducts can also be dealcoholated to a very great extent, by reducing the alcohol content down to values lower than 0.05 mols.

The treatment with the dealcoholating chemical agents is carried out by using an amount of such an agent which is large enough to react with the OH groups present in the alcohol contained in the adduct. Preferably, the treatment is carried out using a slight excess of said agent, which is then removed prior to the reaction of the titanium compound with the thus obtained support.

In the event that the chemical dealcoholation of the $MgCl_2 \cdot pROH$ adduct is carried out by using agents having a reducing activity, for instance an Al-alkyl compound such as Al-triethyl, the thus obtained compound, prior to the reaction with the titanium compound, can be treated with a deactivating agent, for instance O_2 , in order to deactivate the Al-triethyl possibly present therefore avoiding the reduction of the titanium compound.

The treatment with deactivating agents is avoided when one wishes to at least partially reduce the titanium compound. If on the other hand one wishes to reduce the titanium compound to a very great extent, the process for preparing the catalyst component can advantageously comprise the use of reducing agents.

The solid catalyst components obtained according to the methods that comprise the use of $MgCl_2 \cdot pEtOH$ adducts generally show a surface area (by B.E.T. method) generally between 20 and 500 m^2/g and preferably between 50 and 400 m^2/g , and a total porosity (by B.E.T. method) higher than 0.2 cm^3/g preferably between 0.2 and 0.6 cm^3/g . The porosity (Hg method) due to pores with radius up to 10000 Å generally ranges from 0.3 to 1.5 cm^3/g , preferably from 0.45 to 1 cm^3/g .

As explained above the pre-polymerized catalyst component can be obtained by pre-polymerizing the solid catalyst component together with the α -olefin. Said α -olefin is

preferably selected from propylene, butene-1, hexene, 4-methyl-1-pentene, and octene-1.

The use of propylene is particularly preferred.

The pre-polymerization is normally carried out in the presence of an Al-alkyl compound.

The alkyl-Al compound (B) is preferably chosen among the trialkyl aluminum compounds such as for example triethylaluminum, triisobutylaluminum, tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum. ~~It is also possible to use mixtures of trialkylaluminum's with alkylaluminum halides, alkylaluminum hydrides or alkylaluminum sesquichlorides such as AlEt_2Cl and Al_2EtCl_3 .~~

It has been found particularly advantageous to carry out said pre-polymerization using low amounts of alkyl-Al compound. In particular said amount could be such as to have an Al/Ti molar ratio from 0.001 to 50, preferably from 0.01 to 10 and more preferably from 0.05 to 2.5.

The pre-polymerization can be carried out in liquid phase, (slurry or solution) or in gas-phase at temperatures generally lower than 50°C, preferably between -20 and 30°C and more preferably between -10 and 20°C. Furthermore, it is preferably carried out in a liquid diluent in particular selected from liquid hydrocarbons. Among them, pentane, hexane and heptane are preferred.

As explained the so obtained pre-polymerized catalyst components can be used in the (co)polymerization of ethylene, allowing to obtain high activity, polymers with high bulk density and very good morphology. In particular, the catalysts of the invention are endowed with features that render them particularly suitable for the liquid (bulk or slurry) and gas-phase polymerization processes which operate with a pre-polymerization step. In addition, since the catalysts have not aging problems they can be also pre-polymerized in a batch scale and then used in liquid or gas-phase olefin polymerization plants operating without a pre-polymerization line.

In particular, said ethylene (co)polymerization processes can be carried out in the presence of a catalyst comprising (A) the pre-polymerized catalyst component; and (B) an Al-alkyl compound of the type described above.

The above process is suitable for the preparation of wide range of polyethylene products. As an example, the following products can be prepared: high density ethylene polymers (HDPE,

(TC 5431.EP)

having a density higher than 0.940 g/cm^3), comprising ethylene homopolymers and copolymers of ethylene with α -olefins having 3-12 carbon atoms; linear low density polyethylenes (LLDPE, having a density lower than 0.940 g/cm^3) and very low density and ultra low density (VLDPE and ULDPE, having a density lower than 0.920 g/cm^3 , to 0.880 g/cm^3) consisting of copolymers of ethylene with one or more α -olefins having from 3 to 12 carbon atoms, having a mole content of units derived from the ethylene higher than 80%;

The above described polymerization process can be carried out under the polymerization conditions generally known in the art. Accordingly, the polymerization is generally carried out at temperature of from 20 to 120°C , preferably of from 40 to 80°C . In any of the polymerization processes used (liquid or gas-phase polymerization) the catalyst forming components (A) and (B) can be pre-contacted before adding them to the polymerization reactor. Said pre-contacting step can be carried out in the absence of polymerizable olefin or optionally in the presence of said olefin in an amount up to 3 g per g of solid catalyst component. The catalyst forming components can be contacted with a liquid inert hydrocarbon solvent such as propane, n-hexane, or n-heptane at a temperature below about 60°C and preferably from about 0°C to 30°C for a time period of from 10 seconds to 60 minutes.

When a gas-phase polymerization process is used, it can be carried out according to known techniques operating in one or more reactors having a fluidized or mechanically agitated bed. Inert fluids such as nitrogen, or low hydrocarbons like propane, can be used both as a fluidization aid and in order to improve the thermal exchange within the reactors. In addition, also techniques increasing the removal of the reaction heat comprising the introduction of liquids, optionally in mixture with gas, into the reactors, can be used. Preferably the liquids are fresh or make-up monomers. Such techniques are disclosed for example in EP-A-89691, EP-A-241947, USP 5,352,749, WO94/28032 and EPA-695313.

The following examples are given in order better illustrate the invention without limiting it.

EXAMPLES

Characterization

General procedure for the standard propylene polymerization test

A 4 liter steel autoclave equipped with a stirrer, pressure gauge, thermometer, catalyst feeding

(TC 5431.EP)

system, monomer feeding lines and thermostating jacket, was used. The reactor was charged with 0.01 g of solid catalyst component and with TEAL, and cyclohexyl-methyl dimethoxy silane in such amounts to give an Al/Si molar ratio of 4. Moreover, 3.2 l of propylene, and 1.5 l of hydrogen were added. The system was heated to 70°C over 10 min. under stirring, and maintained under these conditions for 120 min. At the end of the polymerization, the polymer was recovered by removing any non-reacted monomers and was dried under vacuum.

Determination of Melt Index

ASTM D 1238 condition "E"

Determination of Xylene Insolubility

2.5 g of polymer were dissolved in 250 ml of o-xylene under stirring at 135°C for 30 minutes, then the solution was cooled to 25°C and after 30 minutes the insoluble polymer was filtered. The resulting solution was evaporated in nitrogen flow and the residue was dried and weighed to determine the percentage of soluble polymer and then, by difference the xylene insoluble fraction (%).

Example 1

PREPARATION OF THE SPHERICAL SUPPORT (ADDUCT $\text{MgCl}_2/\text{EtOH}$) A magnesium chloride and alcohol adduct was prepared following the method described in example 2 of USP 4,399,054, but working at 2000 RPM instead of 10000 RPM.

The adduct containing about 3 mols of alcohol had an average size of about 70 μm .

Preparation of Solid Catalyst Component

The spherical support, prepared according to the general method underwent a thermal treatment, under N_2 stream, over a temperature range of 50-150°C until spherical particles having a residual alcohol content of about 25% (0.69 mole of alcohol for each MgCl_2 mole) were obtained.

Into a 72 l steel reactor provided with stirrer, 44 liters of TiCl_4 at 0°C and whilst stirring 2200 g of the support were introduced. The whole was heated to 130°C over 60 minutes and these conditions were maintained for a further 60 minutes. The stirring was interrupted and after 30 minutes the liquid phase was separated from the settled solid. Thereafter 4 washings with anhydrous hexane (about 22 liters) were performed two of which were carried out at 80°C and two at room temperature.

(TC 5431.EP)

Then, after the addition of 31 liters of anhydrous hexane, 11 liters of a solution of tris(2,4,4-trimethyl-pentyl)aluminum (Tioa) in hexane (100 g/l) were introduced at room temperature into the reactor and stirred for 30 minutes. The liquid phase was separated from the settled solid that was washed with 22 liters of hexane and with 22 liters of heptane (twice for each other) at room temperature.

Thereafter a further treatment with 44 liters of TiCl_4 was performed in the same condition with respect to the first one, and after 4 washings with anhydrous hexane, 2200 g of the spherical solid component were obtained. After drying under vacuum at about 50°C , the solid showed the following characteristics:

- Total titanium	4.52 %	(by weight)
- Ti^{III}	1.2 %	(by weight)
- Al	0.2 %	(by weight)
- Mg	20.0 %	(by weight)
- Cl	71.3 %	(by weight)
- OEt	0.5 %	(by weight)
- porosity (B.E.T.)	0.153 cm^3/g ,	
- surface area (B.E.T.)	50.6 m^2/g	
- total porosity (Hg)	0.692 cm^3/g , 70% of which was due to pores with radius up to 0.1 μm .	

Porosity due to pores with radius up to 1 μm : 0.552

Standard propylene polymerization test

The above-described catalyst component was used in the polymerization of propylene according to the general procedure already described. It was produced a propylene homopolymer having an insolubility in xylene of 83.5%.

Preparation of the pre-polymerized catalyst :

Into a 2.5 liters glass reactor provided with stirrer, 1.5 liters of hexane at $T = 20^\circ\text{C}$ and whilst stirring 40 g of the spherical catalyst were introduced. Keeping constant the internal temperature, 20 g of triisobutylaluminum (TIBA) in hexane (about 20 g/l) were (slowly) introduced at room temperature into the reactor. Then 40 g of propylene were carefully introduced into the reactor at the same temperature (with a propylene partial pressure of 40

mmHg). After 3 hexane washing at $T = 20^{\circ}\text{C}$ (50 g/l), we dried and analyzed the resulting pre-polymerized catalyst that contained 1.1 g of polypropylene per g of catalyst.

Ethylene polymerization (HDPE)

Into a 10 liters stainless steel autoclave, degassed under N_2 stream at 70°C , 4 liters of anhydrous hexane, 0.03 g of pre-polymerized catalyst (containing 0.0135 g of catalyst) and 0.5 g of triisobutylaluminum (Tiba) were introduced. The whole was stirred, heated to 75°C and thereafter 4 bar of H_2 and 7 bar of ethylene were fed. During the polymerization ethylene was fed to keep the pressure constant. After hours the polymerization was discontinued and the collected polymer was dried at 70°C under a nitrogen flow. The activity with respect to the catalyst contained in the pre-polymer was 9.95 kg/g cat/h. The MIE of the polymer was 0.33 and its poured bulk density was 0.363.

Example 2

Preparation of the pre-polymerized catalyst :

The same procedure described in Example 1 was used with the only difference that 40 g of triisobutylaluminum (TIBA) were used. The resulting pre-polymerized catalyst contained 1 g of polypropylene per g of catalyst.

Ethylene polymerization (HDPE)

Into a 10 liters stainless steel autoclave, degassed under N_2 stream at 70°C , 4 liters of anhydrous hexane, 0.041 g of pre-polymerized catalyst component (containing 0.02 g of catalyst) and 0.3 g of triisobutylaluminum (Tiba) were introduced. The whole was stirred, heated to 75°C and thereafter 4 bar of H_2 and 7 bar of ethylene were fed. During the polymerization ethylene was fed to keep the pressure constant. After hours the polymerization was discontinued and the collected polymer was dried at 70°C under a nitrogen flow. The activity with respect to the catalyst contained in the pre-polymer was 9.65 kg/g cat/h. The poured bulk density of the polymer was 0.356

Comparison Example 3

Ethylene polymerization (HDPE)

Into a 10 liters stainless steel autoclave, degassed under N_2 stream at 70°C , 4 liters of anhydrous hexane, 0.0195 g of the non pre-polymerized catalyst component prepared according to the procedure described in Example 1 and 0.3 g of triisobutylaluminum (Tiba)

(TC 5431.EP)

were introduced. The whole was stirred, heated to 75°C and thereafter 4 bar of H₂ and 7 bar of ethylene were fed. During the polymerization ethylene was fed to keep the pressure constant. After hours the polymerization was discontinued and the collected polymer was dried at 70 °C under a nitrogen flow. The activity with respect to the catalyst used was 5.2 kg/g cat/h. The MIE of the polymer was 0.29 and its poured bulk density was 0.336.

Example 4

The spherical support containing about 3 mols of alcohol prepared according to the procedure described in Example 1 underwent a thermal treatment (under N₂ stream), over a temperature range of 50-150°C, until spherical particles having a residual alcohol content about 35% were obtained.

Into a 1600 litres steel reactor provided with stirrer, 350 litres of heptane and 70 Kg of the dealcoholated support were introduced.

The temperature was kept at 20°C while 30.2 Kg of Teal (in heptane 100 g/l solution) were carefully added whilst stirring.

The reactor was heated at 40°C in one hour and these conditions were maintained for a further 120 minutes. The stirring was interrupted and after 30 minutes, the liquid phase was siphoned from the reactor and the settled solid was washed three times with heptane. Then fresh heptane was added to obtain a concentration of 85 g/l.

In a different steel reactor (600 litres of volume), 128.8 Kg of Ti(OBu)₄ were introduced. Then, stirring at 300 rpm and keeping temperature constant at 20°C, 99.8 Kg of SiCl₄ in 105 minutes were added. The resulting solution was stirred for 20 minutes at that temperature.

The whole solution was added into the 1600 litres reactor in 90 minutes at 20°C.

The reactor was heated at 60°C and the conditions were kept constant for 120 minutes. After this period, the stirring was stopped and after 30 minutes the liquid phase was separated from the solid.

The solid was washed eight times with fresh heptane at 70 g/l and then dried under vacuum.

The resulting catalyst component in spherical form exhibited the following characteristics:

Total Titanium	8.4%
Titanium 3+	8.1%

(TC 5431.EP)

Chlorine	48.6%
Magnesium	11.9%
Aluminum	0.2%
EtO- group	7.5%
BuO- group	16.6%

Porosity (mercury) 0.520 cm³/g due to pores with a radius up to 10,000 Å.

Standard propylene polymerization test

The above-described catalyst component was used in the polymerization of propylene according to the general procedure already described. It was produced a propylene homopolymer having an insolubility in xylene of 81%.

Preparation of the pre-polymerized catalyst :

Into a 2.5 liters glass reactor provided with stirrer, 1.5 liters of hexane at 20°C and whilst stirring 40 g of the catalyst prepared as above described were introduced. Keeping constant the internal temperature, 4g of triethylaluminum (TEAL) in hexane (about 20 g/l) were slowly introduced at room temperature into the reactor. Then 160 g of propylene were carefully introduced into the reactor at the same temperature with a propylene partial pressure of 40 mmHg. After 3 hexane washing at a temperature of 20°C (50 g/l), we dried and analyzed the resulting pre-polymerized catalyst that contained 3.2 g of polypropylene per g of catalyst.

Ethylene polymerization (HDPE)

Into a 10 liters stainless steel autoclave, degassed under N₂ stream at 70°C, 4 liters of anhydrous hexane, 0.039 g of pre-polymerized catalyst (containing 0.0078 g of catalyst) and 0.3 g of triethylaluminum (TEAL) were introduced. The whole was stirred, heated to 75°C and thereafter 4 bar of H₂ and 7 bar of ethylene were fed. During the polymerization ethylene was fed to keep the pressure constant. After 2 hours the polymerization was discontinued and the collected polymer was dried at 70 °C under a nitrogen flow. The activity with respect to the catalyst contained in the pre-polymer was 6.5 kg/g cat/h. The MIE of the polymer was 0.44 and its poured bulk density was 0.26.

Example 5

Preparation of the pre-polymerized catalyst :

The same procedure described in Example 4 was used with the only difference that 40 g of

(TC 5431 EP)

propylene were used. The resulting pre-polymerized catalyst contained 0.58 g of polypropylene per g of catalyst.

Ethylene polymerization (HDPE)

Into a 10 liters stainless steel autoclave, degassed under N_2 stream at 70°C, 4 liters of anhydrous hexane, 0.024 g of pre-polymerized catalyst component (containing 0.015 g of catalyst) and 0.5 g of TEAL were introduced. The whole was stirred, heated to 75°C and thereafter 4 bar of H_2 and 7 bar of ethylene were fed. During the polymerization ethylene was fed to keep the pressure constant. After hours the polymerization was discontinued and the collected polymer was dried at 70 °C under a nitrogen flow. The activity with respect to the catalyst contained in the pre-polymer was 5.1 kg/g cat/h. The MIE of the polymer was 0.71 and its poured bulk density was 0.25g/cc.

Comparison Example 6

Ethylene polymerization (HDPE)

Into a 10 liters stainless steel autoclave, degassed under N_2 stream at 70°C, 4 liters of anhydrous hexane, 0.016 g of the non pre-polymerized catalyst component prepared according to the procedure described in Example 4 and 0.3 g of TEAL were introduced. The whole was stirred, heated to 75°C and thereafter 4 bar of H_2 and 7 bar of ethylene were fed. During the polymerization ethylene was fed to keep the pressure constant. After 2 hours the polymerization was discontinued and the collected polymer was dried at 70 °C under a nitrogen flow. The activity with respect to the catalyst used was 3.9 kg/g cat/h. The MIE of the polymer was 0.15 and its poured bulk density was 0.24cc/g.

12.05.2000

16

(41)

CLAIMS

1. A pre-polymerized catalyst component for the polymerization of ethylene optionally in mixtures with olefins $\text{CH}_2=\text{CHR}$, wherein R is a C1-C12 alkyl group, characterized by comprising a non-stereospecific solid catalyst component, comprising a titanium compound and a magnesium dihalide, which is pre-polymerized with an α -olefin $\text{CH}_2=\text{CHR}^1$ wherein R is a C1-C8 alkyl group, to such an extent that the amount of the α -olefin pre-polymer is up to 100g per g of said solid catalyst component.
2. A pre-polymerized catalyst component according to claim 1 in which the amount of the α -olefin polymer is less than 15 g per g of said solid catalyst component.
3. A pre-polymerized catalyst component according to claim 2 in which the amount of the α -olefin polymer is from 0.8 to 4 g per g of solid catalyst component.
4. A pre-polymerized catalyst component according to claim 1 in which the magnesium dihalide is magnesium dichloride in active form and the titanium compound is selected from the compounds of formula $\text{Ti}(\text{OR})_n\text{X}_y$, where R is a C1-C20 hydrocarbon group X is halogen, n is the valence of titanium and y is a number between 1 and n.
5. A pre-polymerized catalyst component according to claim 4 in which the titanium compound is selected from the group consisting of TiCl_4 , TiCl_3 and Ti-tetralcoholates or Ti-chloroalcoholates of formula $\text{Ti}(\text{OR}^n)_a\text{Cl}_{n-a}$ where n is the valence of titanium, a is a number comprised between 1 and n, and R^n is a C1-C8 alkyl or aryl group.
6. A pre-polymerized catalyst component according to claim 1 in which the solid catalyst component to be pre-polymerized has a surface area, by B.E.T. method, between 20 and 500 m^2/g , and a total porosity, by B.E.T. method, higher than 0.2 cm^3/g .
7. A pre-polymerized catalyst component according to claim 1 or 6 in which the solid catalyst component to be pre-polymerized has a porosity (Hg method) due to pores with radius up to 10000 Å 0.3 to 1.5 cm^3/g .
8. A pre-polymerized catalyst component according to any of the preceding claims in

(TC 5431.EP)

12-05-2000

which the solid catalyst component is pre-polymerized with an α -olefin selected from propylene, butene-1, hexene, 4-methyl-1-pentene, and octene-1.

9. A pre-polymerized catalyst component according to claim 8 in which the α -olefin is propylene.

10. A pre-polymerized catalyst component according to any of the preceding claims in which the solid catalyst component to be pre-polymerized is obtained by

(a) reacting a compound $\text{MgCl}_2 \cdot m\text{ROH}$, wherein $0.3 \leq m \leq 1.7$ and R is an alkyl, cycloalkyl or aryl radical having 1-12 carbon atoms, with a titanium compound of the formula $\text{Ti}(\text{OR}^n)_b\text{X}_{y-b}$, in which b is comprised between 0 and 0.5, y is the valence of titanium, X is halogen and R^n has the meaning given above;

(b) reacting the product obtained from (a) with an Al-alkyl compound and,

(c) reacting the product obtained from (b) with a titanium compound of the formula $\text{Ti}(\text{OR}^n)_n\text{X}_{y-n}$, in which n, y, X and R^n have the meanings explained above.

11. A pre-polymerized catalyst component according to any of the claims 1-9 in which the solid catalyst component to be pre-polymerized is obtained by:

(a) the thermal dealcoholation of the adducts $\text{MgCl}_2 \cdot p\text{EtOH}$, where p is a number between 2 to 3.5, until forming adducts in which the alcohol content is reduced to values lower than 2 and preferably comprised between 1.5 and 0.3 mols per mol of magnesium dihalide,

(b) the treatment of said thermally dealcoholated adduct with chemical reagents capable of reacting with the OH groups of the alcohol and of further dealcoholating the adduct until the content is reduced to values which are generally lower than 0.5 mols and

(c) the reaction of said chemically dealcoholated adduct with a Ti compound of formula $\text{Ti}(\text{OR}^n)_n\text{X}_y$, where X, R^n , n, and y have the same meanings described above.

12. A pre-polymerized catalyst component according to any of the preceding claims in which said pre-polymerization is carried out using amounts of alkyl-Al compound such as to have an Al/Ti molar ratio from 0.001 to 50, preferably from 0.01 to 10.

13. A pre-polymerized catalyst component according to claim 12 in which the Al-alkyl

(TC 5431.EP)

compound is a trialkyl aluminum compound.

14. A pre-polymerized catalyst component according to claim 13 in which the trialkyl aluminum compound is selected from triethylaluminum, triisobutylaluminum, tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum.
15. A process for the (co)polymerization of ethylene characterized in that it is carried out in the presence of a catalyst comprising (A) a pre-polymerized catalyst component according to any of the preceding claims; and (B) an Al-alkyl compound.
16. A process according to claim 15 in which ethylene is copolymerized with olefins $\text{CH}_2=\text{CHR}$, wherein R is a C1-C12 alkyl group.

ABSTRACT

Catalyst components for the preparation of ethylene (co)polymers capable to produce polymers with high bulk density, to avoid the problems of formation of fines and that have a high activity are provided. Said catalyst components are characterized by comprising a non-stereospecific solid catalyst component, comprising a titanium compound and a magnesium dihalide, which is pre-polymerized with an alpha olefin $\text{CH}_2=\text{CHR}^1$ wherein R is a C1-C8 alkyl group, to such an extent that the amount of the α -olefin pre-polymer is up to 100g per g of said solid catalyst component.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☒ **SKEWED/SLANTED IMAGES**
- ☒ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.